

RÄUCHERGOLD

Natural wood fibers

Basic raw material

Selected leaf wood

Chemical and physical properties

Colour	light brown
Structure	cubic
Average particle size / particle range	6 mm - 10 mm
Oxide ash (850 °C, 4 h)	~ 1 %
pH-value (10 % suspension)	4 - 6
Bulk density (in accordance with DIN EN ISO 60)	220 g/L - 320 g/L

Screen analysis (with RETSCH vibrating sieve) with an interior mesh aperture of:

> 15 mm	> 8 mm	> 5 mm
max. 5 %	max. 15 %	max. 70 %

General remarks

RÄUCHERGOLD wood fibers are environment friendly products, gained from replenishable raw materials.

As with all natural products slight differences to the above given values may arise.

Release date: 2022-08 / 1 page



Fibers for Life.

J. RETTENMAIER & SÖHNE GMBH + CO KG
Holzmühle 1
73494 Rosenberg (Germany)

Phone: +49 7967 152-0
info@jrs.de • www.jrs.de