

RÄUCHERGOLD

Natural wood fibers

Basic raw material

Selected leaf wood

Chemical and physical properties

Colour	light brown
Structure	cubic
Average particle size / particle range	1.2 mm - 1.8 mm
Oxide ash (850 °C, 4 h)	~ 1 %
pH-value (10 % suspension)	4.5 - 6.5
Bulk density (in accordance with DIN EN ISO 60)	260 g/L - 320 g/L

Screen analysis (with RETSCH vibrating sieve) with an interior mesh aperture of:

<u>> 2.5 mm</u>	<u>> 1.6 mm</u>	<u>> 1 mm</u>
max. 8 %	20 % - 60 %	80 % - 100 %

General remarks

RÄUCHERGOLD wood fibers are environment friendly products, gained from replenishable raw materials.

As with all natural products slight differences to the above given values may arise.

Release date: 2022-08 / 1 page