

|                                                                                   |                                                                            |                                                                                       |                                                |
|-----------------------------------------------------------------------------------|----------------------------------------------------------------------------|---------------------------------------------------------------------------------------|------------------------------------------------|
|  | Spezifikation - Specification                                              |                                                                                       | KONOS GmbH<br>Fabrikstraße 8<br>D-01683 Nossen |
|                                                                                   | Korb-Kaffeefilter, weiß oder braun<br>Basket Coffee filter, white or brown |                                                                                       |                                                |
| Papier - Paper                                                                    |                                                                            |                                                                                       |                                                |
| Flächengewicht, Basis weight:                                                     | DIN EN ISO 536                                                             | 39 ± 2 g/m <sup>2</sup>                                                               |                                                |
| Dicke, Thickness:                                                                 | DIN EN 20 534, ISO 534                                                     | 0,12 ± 0,02 mm                                                                        |                                                |
| Bruchkraft längs, Tensile strength MD:                                            | DIN EN ISO 1924-2                                                          | ≥ 15 N/15 mm                                                                          |                                                |
| Bruchkraft quer, Tensile strength CD:                                             | DIN EN ISO 1924-2                                                          | ≥ 8 N/15 mm                                                                           |                                                |
| Naßbruchkraft längs, Tensile strength MD, wet:                                    | DIN ISO 3781                                                               | ≥ 3,5 N/15 mm                                                                         |                                                |
| Bruchdehnung längs, Stretch MD:                                                   | DIN EN ISO 1924-2                                                          | ≥ 3,0 %                                                                               |                                                |
| Filtriergeschwindigkeit, Filtration speed:                                        | DIN 53 137:<br>Herzberg:                                                   | 4,0 ± 1,5 s/10 ml<br>30 ± 5 s/100 ml                                                  |                                                |
| Kaffeefilter - Coffee filter                                                      |                                                                            |                                                                                       |                                                |
| Maße, Dimensions:                                                                 |                                                                            | Größe, Size:                                                                          |                                                |
| Blatt-/Außendurchmesser, Sheet/Outside diameter:                                  |                                                                            | 250 ± 5 mm                                                                            |                                                |
| Innendurchmesser, Inside diameter:                                                |                                                                            | 84 ± 10 mm                                                                            |                                                |
| Nossen, 18.02.2026                                                                | KONOS GmbH<br>Fabrikstraße 8<br>01683 Nossen                               |  |                                                |
| F.Proft ( Quality)                                                                |                                                                            |                                                                                       |                                                |